

IN THE ABSTRACT

Please amend the Abstract on page 44 as follows:

--ABSTRACT

[Provided are a] A color pigment master batch having a high recycling property and a process for producing a blow-molded article having a grain-tone appearance using this color pigment master batch. [Disclosed is a] The color pigment master batch for blow molding [comprising] ~~includes~~ a pigment and a carrier resin[, wherein used as a] . The carrier resin is a thermoplastic elastomer which is a crystalline or amorphous thermoplastic elastomer having a Vicat softening point higher than a melting temperature of a molding base resin and a crystal melting point or a flow-starting temperature higher by 20°C or more than a melting temperature of the molding base resin and in which an MFR ratio thereof to the molding base resin is 5 or more.--